

TECHNICAL SHEET

Ag38MnNi TR

Product name

Ag38MnNi TR

Class of product

Three-layered strip of silver brazing alloy, cadmium free

Corresponding standards (external brazing layers)

ISO 17672 -----
EN1044 -----
AWS A5.8-04 -----
DIN 8513 -----

Nominal composition of external brazing layers (weight %)

Ag: 38
Cu: 26
Zn: 24
Ni: 4,5
Mn: 7,5

Physical and technical properties

Melting range (Solidus – Liquidus): 650 – 690 °C
Brazing temperature: 700 °C
Density: 8,9 g/cm³
Ratio: 1:2:1

Range of application

Ag38MnNi TR is a special application, cadmium-free, silver brazing alloy with good flow properties.

Only available as a strip, it consists of two layers of silver brazing alloy clad onto a copper core.

It is ideal for brazing carbides onto steels, especially large pieces.

The copper core of the strip absorbs and relieves the stresses caused by the difference in thermal expansion between carbide and base metal, thus helping to prevent cracking phenomena.

Brazing procedures range from manual to induction, and to resistance techniques.

When brazing in an oxidizing environment a proper flux should be used (AG7 and/or AG8 are recommended).

The main applications of this alloy are found in the tool industry for the brazing of carbide tipped tools, particularly wood-working tools, and/or any tool subject to in-service impact stresses.

Characteristics Make-up

Strips: Thickness: 0,1 ⇒ 1 mm Width: 1,3 ⇒ 80 mm
Preforms from Strip

Other dimensions are available upon request.

NOTE:

Information contained in this data sheet are based on the knowledge available to us at the date of last document revision and are believed to be accurate. Anyway, no data contained in this data sheet may be regarded as an assurance of any property of the product. We do not assume any responsibility for results obtained or damages occurred from the use of the information contained in this data sheet. We do not assume any responsibility for any un-proper use of the product. Users should verify the suitability and completeness of information with regard to specific use the product. As end use of product is not under our direct control, it is the user's responsibility to fully comply with applicable laws and regulations in safety and hygiene.

STELLA s.r.l.

Via Marconi 26 – 21041 ALBIZZATE (VA) – ITALY

Tel. +39-0331-985787 – Fax +39-0331-985803

info@stella-welding.com - www.stella-welding.com